

# スポット封孔剤 アルタッチ1180シリーズ

Spot sealant ALTOUCH 1180 series



## ■特長・用途

アルタッチ1180シリーズは、アクリル系常温一液型嫌気性タイプのスポット封孔剤です。隙間やピンホールに浸透させると、空気の遮断により化学反応が促進され、硬質の高分子硬化物となり封孔します。アルタッチ1180シリーズは取り扱いが簡単で、必要な箇所を必要な分だけ処理できるため環境に優しい商品です。

## ■使用方法

- ①対象となる箇所、基材の水分、油分、錆などを除去し、乾いた状態にしてください。
- ②空気を遮断することで硬化します。  
空気の触れている部分は硬化しません。  
硬化時間を短縮する為の硬化促進剤（別売り）も用意しています。  
硬化促進剤を使用する場合  
硬化促進剤を滴下し、5~10分放置した後に主剤を滴下してください。

## ■Characteristics and Application

The ALTOUCH 1180 series is an acrylic, room temperature hardening, single component and anaerobic type spot sealant. When penetrated into gaps or pinholes, the chemical reaction is accelerated by cutout of air, and it becomes a hard and highly polymerized hardened material, sealing these gaps or pinholes. The ALTOUCH 1180 series is easy to use, allows treating only necessary spots and necessary amount, and therefore, it is an environmental friendly product.

## ■Application method

- ①Eliminate moisture, oil content, rust etc. from the zone or base materials where to apply; and leave there dried.
- ②It has a function to harden when the air is cut. Where exposed to the air will not harden.  
We also offer a hardening accelerator (sold separately) to shorten the curing time.  
When using a hardening accelerator  
Add the hardening accelerator and leave it for 5 to 10 minutes before adding the base agent.

## ■性能比較表 / Performance comparison table



製品名 Product name	アルタッチ1180 ALTOUCH 1180	アルタッチ1180V ALTOUCH 1180V	アルタッチ1185 ALTOUCH 1185
成分 Composition	変性アクリルモノマー Denaturated acrylic monomer	変性アクリルモノマー Denaturated acrylic monomer	変性アクリルモノマー Denaturated acrylic monomer
密度 Density	1.08~1.10g/cm <sup>3</sup>	1.08~1.10g/cm <sup>3</sup>	1.11~1.13g/cm <sup>3</sup>
粘度 Viscosity	10~15mPa·s	400~600mPa·s	30~35mPa·s
外観 External aspect	緑色液体 Green liquid	緑色液体 Green liquid	黄褐色液体 Yellow brown liquid
固形分 Solid content	100%	100%	100%
硬化時間 Curing time	720分 ※30分 720min ※30min	720分 ※30分 720min ※30min	360分 ※30分 360min ※30min
分解温度 Decomposition Temperature	200℃	250℃	220℃
金属 Metal	○	○	○
樹脂 Plastic	×	×	×
ガソリン Gasoline	○	○	○
ATF	○	○	○
LLC	○	○	○
モーターオイル Motor oil	○	○	○

※硬化促進剤を使用した場合 / When using hardening accelerator

## ■荷姿 / Packing style

アルタッチ1180, 1180V, 1185 ALTOUCH 1180, 1180V, 1185	Net.50g	スポイトボトル Bottle with syringe
硬化促進剤 Hardening accelerator	Net.40g	褐色瓶 Brown bottle